

B1 sub 1 1. (Once amended) A multilayer, biaxially oriented polypropylene film comprising a base layer and at least one heat-sealable top layer, wherein said base layer comprises (i) a propylene polymer and (ii) a combination of a hydrocarbon resin and a wax, said resin having a mean molecular weight Mw of from 600 to 1500 and said wax having a mean molecular weight Mn of from 200 to 700.

2. (Once amended) A polypropylene film as claimed in claim 1, wherein a n-heptane-insoluble content of the propylene polymer of the base layer has a chain isotacticity index, measured by means of C-NMR spectroscopy, of at least 95%.

B2 3. (Twice amended) A polypropylene film as claimed in claim 1, wherein the propylene polymer has Mw/Mn of from 1 to 10.

B3 5. (Twice amended) A polypropylene film as claimed in claim 1 wherein said resin is selected from the group consisting of an unhydrogenated styrene polymer, a methylstyrene-styrene copolymer, a pentadiene copolymer, a cyclopentadiene copolymer, an  $\alpha$ -pinene polymer, a  $\beta$ -pinene polymer, a colophony, colophony derivatives, terpene polymers, hydrogenated compounds of terpene polymers, a hydrogenated  $\alpha$ -methylstyrene-vinyltoluene copolymer, and mixtures thereof.

11. (Twice amended) A polypropylene film as claimed in claim 10, wherein the polymer of the top layers has been peroxidically degraded and the degradation factor is in the range from 3 to 15.

B4 12. (Twice amended) A polypropylene film as claimed in claim 10, wherein an interlayer of  $\alpha$ -olefinic polymers has been applied to one or both sides between the base layer and the top layers.

13. (Twice amended) A polypropylene film as claimed in claim 1, wherein the total thickness of the film is from 4 to 60  $\mu\text{m}$  and the base layer makes up from about 40 to 60% of the total thickness.

14. (Twice amended) A polypropylene film as claimed in claim 20, wherein the base layer comprises a tertiary aliphatic amine as an antistatic.

B4  
Control

15. (Twice amended) A polypropylene film as claimed in claim 21, wherein the top layer comprises polydimethylsiloxane as a lubricant and SiO<sub>2</sub> as an antiblocking agent.

16. (Twice amended) A polypropylene film as claimed in claim 1, wherein all layers of the film further comprise neutralizers and stabilizers.

B 5

17. (Once amended) A process for the production of a polypropylene film as claimed in claim 1, which comprises performing a orientation in the longitudinal direction with a longitudinal stretching ratio of from 5:1 to 9:1 and in the transverse direction with a transverse stretching ratio of from 5:1 to 10:1.

20. (New) The polypropylene film as claimed in claim 1, wherein the base layer further comprises at least one additive selected from the group consisting of neutralizers, stabilizers, antistatics and lubricants.

B6

21. (New) The polypropylene film as claimed in claim 1, wherein the top layer further comprises at least one additive selected from the group consisting of neutralizers, stabilizers, antistatics, lubricants and anti-blocking agents.

22. (New) The polypropylene film as claimed in claim 13, wherein the total thickness of the film is from 5 to 30  $\mu\text{m}$ .

23. (New) The polypropylene film as claimed in claim 13, wherein the total thickness of the film is from 6 to 25  $\mu\text{m}$ .

5/20/08

24. (New) A process for the production of oriented polypropylene films having an improved water vapor barrier action, which comprises compressing a polymer or a polymer

mixture, said polymer or polymer mixture containing a resin having a mean molecular weight Mw of from 600 to 1500 and a wax having a mean molecular weight Mn of from 200 to 700.

25. (New) A packaging film produced by the process of claim 24.

26. (New) The polypropylene film as claimed in claim 11, wherein the degradation factor is in the range from 6 to 10.

27. (New) A polypropylene film as claimed in claim 6, wherein the hydrocarbon resin is present in an amount of from 5 to 12% by weight, based on the weight of the base layer.

28. (New) A polypropylene film as claimed in claim 7, wherein the wax is present in an amount of from 1 to 8% by weight, based on the weight of the base layer.

29. (New) A polypropylene film as claimed in claim 7, wherein the wax is present in an amount of from 1 to 6% by weight, based on the weight of the base layer.

30. (New) A multilayer, biaxially oriented polypropylene film comprising a base layer and at least one heat-sealable top layer, wherein said base layer comprises (i) a propylene polymer and (ii) a combination of a resin and a wax,  
wherein said resin being a hydrocarbon resin, fully or partially hydrogenated, having a softening point of 80°C or above and having a mean molecular weight Mw of from 600 to 1500;  
and  
said wax being selected from the group consisting of polyethylene waxes, macrocrystalline paraffin waxes, microcrystalline paraffins and mixtures thereof and having a mean molecular weight Mn of from 200 to 700.

31. (New) A polypropylene film as claimed in claim 29, wherein said hydrocarbon resin is selected from the group consisting of petroleum resins, styrene resins, cyclopentadiene resins, terpene resins and mixtures thereof.